

SEDE

Via Martelli, 26 - 40138 Bologna
Tel. 051 534015 - Fax. 051 530085

CERTI.CER.

LABORATORIO DI ZONA

Via Valle d'Aosta, 1 - 41049 Sassuolo
Tel. 0536 802154

Part. IVA 0094778-0375

Bologna, 13/06/07

TEST REPORT N° **5335/07**

(translation of test report Nr. 4997/07 of 13/06/07)

concerning ceramic tiles according to
EN 14411 (ISO 13006)

Requested by:	LAMINAM S.p.A. – Via Ghiarola Nuova, 258 – 41042 FIORANO MODENESE (MO)
On (date):	21/05/07
For the sample marked:	Unglazed ceramic slabs marked "SKETCH MORO – 1 x 3 m x 3 mm".

UNI EN ISO 10545-6 - Determination of resistance to deep abrasion
(Unglazed tiles)

Test specimens	1A	1B	2A	2B	3A	3B	4A	4B	5A	5B
l, chord length (mm)	25,5	25,5	26,0	26,0	26,0	26,0	26,0	26,0	25,5	26,0
V, abraded volume (mm ³)	139	139	147	147	147	147	147	147	139	147

Average volume, Vm (mm³):

145

Prof. Ing. Giorgio Timellini
Director

The results reported relate only to the samples tested. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. The reproduction of this test report is only authorized in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction. This test report consists of 1 pages, this cover included.



Consorzio universitario per la gestione del
«Centro di ricerca e sperimentazione per
l'industria ceramica».
D.P.R. 10-4-1978 n. 806
(G.U. 20-12-1978 n. 353)

Laboratorio autorizzato ad effettuare il
servizio di rilevamento dell'inquinamento
atmosferico.
Decreto MINISTERO SANITÀ 10-8-1974
(G.U. 14-9-1974 n. 240)

Laboratorio iscritto nell'albo dei «Laboratori Esterni
Pubblici e Privati Altamente Qualificati».
Decreto MINISTERO RICERCA SCIENTIFICA 6-6-1983
(G.U. 6-7-1983 n. 183)

Membro ASTM
American Society for
Testing and Materials.